

FLS 103 PVC primer

Product Description

FLS 103 PVC Primer is a one component, low viscosity material designed to clean and prime existing and new PVC membranes prior to the application of FLS 104 / FLS 105 Liquid waterproofing. Apply with brush or roller at a maximum consumption rate of 100g per m².

Features & Benefits

- One component
- Low viscosity
- Extremely quick curing time

Application Procedure

Clean the surface as per manufacturer's recommendations. Remove oil, grease and wax contaminants. Apply only when atmospheric and substrate temperatures are greater than 5°C. the surface of the substrate should be clean and dry, and must be 3°C about the dew point. If the surface is below or at dew point temperature then moisture can form on the surface and affect coating adhesion and curing. Apply with brush or roller at a maximum consumption rate of 100g per m². Main coat may be applied as soon as primer is no longer tacky (approximately 15 to 30 minutes).

Cleaning

Clean tools and equipment first with paper towels and then using FF860 Solvent Cleaner. Rollers will not be re-usable.

Packaging

5 litres

Shelf Life

Can be kept for 12 months maximum in the original unopened tins in dry places and at temperatures of 5°C to 25°C. Once opened, use as soon as possible.

Safety Information

FLS 103 PVC Primer contains volatile flammable solvents. You are advised to observe the standard safety rules: Apply in well ventilated, non smoking areas and away from naked flames. In closed spaces, use ventilators and respiratory equipment / fitted face masks. Refer to MSDS for further information.

Technical specifications

In liquid form (before application):

Property	Units	Method	Specification
Viscosity (Brookfield)	cP	ASTM D2196-86, @ 25 °C	50-150
Specific weight	gr/cm ³	ASTM D1475 / DIN 53217 / ISO 2811, @ 20°C	0.8-0.9